

KemaPox DBP

Description di-n-butyl phthalate

Fields of applications:

- **KemaPox DBP** used as plasticizers in selected epoxy resin formulations in solvent-free systems.

Specification:

Viscosity at 23 °C	app 20 mPas	DIN 53214
Density at 23 °C	1.046 g/cm ³	DIN 51757,T3
Color index	max 30	DIN ISO 6271

Characteristic data:

Acid Value	max 0.1 mg KOH/g	EN ISO 2114
Ester Content	99.5 min %	by area gas chromatography
water Content	0.1 max	DIN 51777

Storage life: It is at least 24 months, at room temperature in the original sealed containers, from the date of manufacture.

Handling Precautions: Please refer to the Safety data sheet of this product.

The information provided herein is considered to be representative of our production, and is to the best of our knowledge accurate and according to our laboratory tests and data which we believe to be reliable. This does not construe in any way any liability or responsibility from our part for any third party since the conditions of use are beyond our control and each user should perform sufficient investigation to establish the full suitability of our products for its intended use. Furthermore no information provided here should be taken as a recommendation or advice for infringement of third party intellectual property rights.