

**KemaPox HF 023**

**Description:** AR aliphatic polyamine curing agent - Meta Xylene Diamine

**Fields of applications:**

- **KemaPox HF 023** is mainly used in combination with suitable epoxy resin formulations for solvent-free systems.

**Specification:**

Appearance	clear liquid	
Content	> 99 %	
Color (APHA)	max 30	DIN/ISO 6271

**Characteristic data:**

H*-equivalent mass	34	
Viscosity at 23 °C	6.8 mPas	DIN 525672
Density at 23 °C	1.052 g/cm <sup>3</sup>	DIN 53217
Flash point	139 °C	DIN-52758
Boiling point	247 °C	
Solid Content	100%	

**Storage life:** It is at least 24 months, at room temperature in the original sealed containers, from the date of manufacture.

**Handling Precautions:** Please refer to the Safety data sheet of this product.

Classification: C "corrosive".

*The information provided herein is considered to be representative of our production, and is to the best of our knowledge accurate and according to our laboratory tests and data which we believe to be reliable. This does not construe in any way any liability or responsibility from our part for any third party since the conditions of use are beyond our control and each user should perform sufficient investigation to establish the full suitability of our products for its intended use. Furthermore no information provided here should be taken as a recommendation or advice for infringement of third party intellectual property rights.*