

KemaPox RL 215

Description: Specially modified, low-viscous epoxy resin with bifunctional reactive-thinner.

Fields of applications:

 KemaPox RL 215 is a modified epoxy resin with very high mechanical and chemical properties and as such is used for many different applications with little or no change to the original unmodified epoxy resin properties

Specification:

Viscosity at 23 °C	app 900 mPas	DIN 53214
Density at 23 °C	1.14 g/cm ³	DIN 51757,T3
Color index	< 1	Gardner

Characteristic data:

Epoxy Equivalent Wt. 18	80	
Epoxy Value ap	pp. 055 eq./100g	

<u>Storage life:</u> It is at least 24 months, at room temperature in the original sealed containers, from the date of manufacture.

Handling Precautions: Please refer to the Safety data sheet of this product.

Classification: C "corrosive".

The information provided herein is considered to be representative of our production, and is to the best of our knowledge accurate and according to our laboratory tests and data which we believe to be reliable. This does not construe in any way any liability or responsibility from our part for any third party since the conditions of use are beyond our control and each user should perform sufficient investigation to establish the full suitability of our products for its intended use. Furthermore no information provided here should be taken as a recommendation or advice for infringement of third party intellectual property rights.

TI RL215

05-06. Ver. 06