

KemaPox RL 216

Description: Specially modified low-viscous epoxy resin

Fields of applications:

- **KemaPox RL 216** is a modified epoxy resin, especially recommended to be used for primer and coating systems.
- It is used with water dilutable epoxy hardener systems.

Specification:

| | | |
|--------------------|------------------------|--------------|
| Viscosity at 23 °C | app 1000 mPas | DIN 53214 |
| Density at 23 °C | 1.11 g/cm ³ | DIN 51757,T3 |
| Color index | < 1 | Gardner |

Characteristic data:

| | | |
|----------------------|--------------------|--|
| Epoxy Equivalent Wt. | 196 | |
| Epoxy Value | app. 0.51 eq./100g | |

Storage life: It is at least 24 months, at room temperature in the original sealed containers, from the date of manufacture.

Handling Precautions: Please refer to the Safety data sheet of this product.

Classification: C "corrosive".

The information provided herein is considered to be representative of our production, and is to the best of our knowledge accurate and according to our laboratory tests and data which we believe to be reliable. This does not construe in any way any liability or responsibility from our part for any third party since the conditions of use are beyond our control and each user should perform sufficient investigation to establish the full suitability of our products for its intended use. Furthermore no information provided here should be taken as a recommendation or advice for infringement of third party intellectual property rights.