

KemaPox RL 508

Description: Monofunctional reactive diluent consisting of alkyl (C12-C14) glycidylether having very good thinning effect and slight influence on thermal, mechanical and electrical properties in the cured state of the epoxy system

Fields of applications:

- **KemaPox RL 508** Reduction of viscosity in epoxy systems, enhancing their processing, impregnating and wetting properties.

Specification:

Viscosity at 23 °C	app 7 mPas	DIN 53214
Density at 23 °C	0.89 ± 0.02 g/cm ³	DIN 51757,T3
Color index	< 1	Gardner

Characteristic data:

Epoxy Equivalent Wt.	286-308	gm. /equivalent
Epoxy Value	app. 0.34	eq./100g
Epichlorohdrine cont.	< 5 ppm	

Storage life: It is at least 24 months, at room temperature in the original sealed containers, from the date of manufacture.

Handling Precautions: Please refer to the Safety data sheet of this product.

The information provided herein is considered to be representative of our production, and is to the best of our knowledge accurate and according to our laboratory tests and data which we believe to be reliable. This does not construe in any way any liability or responsibility from our part for any third party since the conditions of use are beyond our control and each user should perform sufficient investigation to establish the full suitability of our products for its intended use. Furthermore no information provided here should be taken as a recommendation or advice for infringement of third party intellectual property rights.